



2013 Second Quarter Production Summary for Yauricocha Mine

Yauricocha Production	3 Months Ended			6 Months Ended		
	June 30, 2013	June 30, 2012	% Var.	June 30, 2013	June 30, 2012	% Var.
Tonnes processed	206,407	217,078	-5%	421,274	429,015	-2%
Daily throughput	2,359	2,481	-5%	2,407	2,452	-2%
Polymetallic	158,500	150,486	5%	325,185	273,679	19%
Silver grade (g/t)	85.79	105.94	-19%	87.90	102.77	-14%
Copper grade	0.67%	0.77%	-13%	0.73%	0.76%	-3%
Lead grade	1.40%	1.90%	-26%	1.46%	1.92%	-24%
Zinc grade	3.91%	3.88%	1%	3.98%	4.08%	-3%
Gold Grade (g/t)	0.69	0.78	-12%	0.69	0.81	-14%
Silver recovery	69.85%	70.02%	0%	69.92%	68.96%	1%
Copper recovery	73.19%	66.76%	10%	73.94%	63.86%	16%
Lead recovery	79.00%	81.71%	-3%	80.17%	80.26%	0%
Zinc recovery	88.58%	88.96%	0%	88.28%	89.14%	-1%
Gold Recovery	17.11%	19.32%	-11%	17.83%	17.80%	0%
Lead Oxides	47,908	51,165	-6%	96,089	103,173	-7%
Silver grade (g/t)	318.51	376.47	-15%	290.65	364.21	-20%
Lead grade	8.35%	7.05%	18%	7.35%	6.81%	8%
Gold grade (g/t)	2.06	3.43	-40%	1.82	3.45	-47%
Silver recovery	35.95%	26.17%	37%	34.87%	26.70%	31%
Lead recovery	62.69%	48.03%	31%	60.27%	48.54%	24%
Gold Recovery	37.87%	35.38%	7%	37.46%	35.57%	5%
Copper Deposits	0	15,428	-100%	0	52,164	-100%
Silver grade (g/t)	0.00	88.13	-100%	0.00	89.01	-100%
Copper grade	0.00%	1.65%	-100%	0.00%	1.88%	-100%
Gold grade (g/t)	0.00	1.07	-100%	0.00	1.05	-100%
Silver recovery	0.00%	56.80%	-100%	0.00%	60.96%	-100%
Copper recovery	0.00%	89.31%	-100%	0.00%	89.61%	-100%
Gold recovery	0.00%	27.94%	-100%	0.00%	32.03%	-100%
Silver (oz)	481,058	544,707	-12%	955,660	1,037,139	-8%
Copper (000 lb)	1,714	2,212	-23%	3,889	4,846	-20%
Lead (000 lb)	9,382	8,958	5%	17,761	16,804	6%
Zinc (000 lb)	12,121	11,465	6%	25,167	21,950	15%
Gold (oz)	1,800	2,876	-37%	3,398	5,901	-42%